

10/531690

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
29 April 2004 (29.04.2004)

PCT

(10) International Publication Number  
WO 2004/035853 A1

(51) International Patent Classification<sup>7</sup>: C23C 8/22,  
C21D 1/76

(21) International Application Number:  
PCT/PL2003/000066

(22) International Filing Date: 2 July 2003 (02.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
356754 21 October 2002 (21.10.2002) PL

(71) Applicants (for all designated States except US):  
SECO/WARWICK SP. Z O.O. [PL/PL]; ul. Sobieskiego  
8, PL-66-200 Swiebodzin (PL). POLITECHNIKA  
LÓKZKA [PL/PL]; ul. Stefanowskiego 1/15, PL-90-924  
Łódź (PL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): KULA, Piotr

[PL/PL]; ul. Chochola 43, PL-91-230 Łódź (PL). OLE-  
JNIK, Józef [PL/PL]; Osiedle Zaków 61, PL-66-200  
Swiebodzin (PL). HEILMAN, Paul [DE/DE]; Tiedstrasse  
8, 63469 Maintal (DE).

(74) Agent: NISZTUK, Helena; Lubuski Klub Techniki i  
Racjonalizacji, ul. Niecala 2F, PL-65-245 Zielona Góra  
(PL).

(81) Designated State (national): US.

(84) Designated States (regional): European patent (AT, BE,  
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,  
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: HYDROCARBON GAS MIXTURE FOR THE UNDER-PRESSURE CARBURIZING OF STEEL

(57) Abstract: The subject of present invention relates to mixture for carburizing of steel products, mainly parts of machines, vehi-  
cles and every mechanical apparatus, used in vacuum furnaces. Present invention relates to mixture for under-pressure carburizing  
containing the carbon carrier comprising two unsaturated hydrocarbons, likely ethylene and acetylene, in volume ratio from 0.1 to  
2.00. The carbon carrier can be further mixed with hydrogen or ammonia.

WO 2004/035853 A1